

# Sol & Send

	Dimensions and Basic Data	Standard	Result
	SIZE 24342	EN ISO	<b>PLANK:</b> <b>6.5 x 1220 x 180 mm - Prime look</b> 10 planks/box = 2,20 m <sup>2</sup> /box  <b>6.5 x 1524 x 180 mm - Rustic look</b> 8 planks/box = 2,19 m <sup>2</sup> /box  <b>6.5 x 600 x 120 mm - Prime look, herringbone</b> 16 planks/box = 1,15 m <sup>2</sup> /box  <b>TILE:</b> <b>6.5 x 305 x 610 mm</b> 8 tiles/box = 1,49 m <sup>2</sup> /box
	THICKNES	EN ISO 24346	6.5 MM
	WEAR LAYER	EN ISO 24340	0.70 MM
	LOCKING METHOD		CLIC-system
	SURFACE TREATMENT		PU coating + protected with aluminium oxide (anti-scratch) and stain resistant technology.
	CORE		CORE Sound reducing water resistant rigid core, SPC
<b>Technical Data</b>			
	BEVELLED EDGE	MICRO	4 Sides
	MASS		10.80 kg/m <sup>2</sup>
	STANDARD S	EN 649/ EN ISO 10582	Pass
	CLASSIFICATION	EN 685 / EN ISO 10874 - Light industrial	42: Light industrial general
		EN 685 / EN ISO 10874 - Commercial	33: Commercial heavy
		EN 685 / EN ISO 10874 - Domestic	23: Domestic heavy
	REACTION TO FIRE	EN 13501-1	B <sub>s</sub> -s <sup>1</sup>
	STAINING RESISTANCE	EN 423	Pass
	LIGHT FASTNESS	EN ISO 105-B02	>6
	DIMENSIONAL STABILITY	EN 434 / EN ISO 23999	≤ 0.10 %

# Sol & Send

	ACOUSTIC IMPACT - NOISE REDUCTION	EN ISO 717-2/ EN ISO 140-8	ΔL <sub>w</sub> = 19DB
	ELECTRICAL BEHAVIOR - BODY VOLTAGE	EN 1815	Pass
	IDENTATION - RESIDUAL	EN 433 / EN ISO 24343-1	ss ≤ 0.1 mm
	CASTOR CHAIR - CONTINUOUS USE	EN 425 / ISO 4918	Pass
	THERMAL RESISTANCE	EN1266 7	<0.15 (m <sup>2</sup> K/W)
	SLIP RESISTANCE*	BS 7976-2:2002	Plank: Dry: 62, Wet: 50
	WEAR RESISTANCE	EN 660-2	T
	IMPACT RESISTANCE	EN1332 9	≥ 1200 mm
	CLICK TENSION	Internal	200 N/5 cm
	SWELLING	ISO 24336	Pass
	FLOOR HEATING	Appropriate for all standard heating systems in cement flooring.	Not appropriate for heating films.
<b>Dangerous substances</b>			
	VOC EMISSION	French VOC Regulation (ISO 16000)	A+
	E1 FORMALDEHYDE - HCHO EMISSION		EN1404 1
	REACH		Friendly reach compliant

\* Slip resistance is measured on ex-factory product. Slip resistance can be affected by surface contamination, use and how the product is maintained.